


SPARCOTM
PAINTS



**SPARCO SILK TOUCH
EMULSION
TDS**



Sparco Silk Touch Emulsion



Packing Size

0.91, 3.64, 14.56 Ltr.

Handling

Handle with care. stir well before use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Health and Safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

Typical Paint System

Sparco Water based Primer 1-2 coat
Sparco wall Putty 1-2 coats
Sparco Silk Touch Emulsion 2-3 coats

Product Description

Sparco Silk touch emulsion is a good quality PVA based interior emulsion with high spreading rate tough & durable film. It contains anti fungal & anti bacterial additives. It exhibits good brush & recoat ability. It gives good flow and a smooth flat finish for new & previously painted interior surface.

Recommended Use

It can be used on variety of interior surfaces such as cement plaster, Putty filler, gypsum board, concrete, asbestos cement sheeting, rendered block work. Available in wide range of colors.

Film Thickness and Spreading Rate

Dry film thickness	30-35 microns
Wet film thickness	70-75 microns
Theoretical Spreading Rate	12-14 m ² /litr/coat

Physical Properties

Colour	As per Shade Card
Finish	Matt
Volume solids	45 ± 5
Flash Point	N.A
Specific Gravity	1.45-1.65

Surface Preparation

The substrate must be sound, clean, dry, free from dust, oil and grease etc. it can be either pre-primed or smooth surface. All traces of release agents must be removed. On chalky and dusty surfaces, all loose material must be removed by stiff bristle brushing.

Application Methods



Drying Time

Temperature	Touch Dry	Recoating Interval	Hard Dry
23 °C	40 min	4 hours	6 hours
30 °C	30 min	3 hours	4 hours
38 °C	20 min	2 hours	2 hours

Application Data

System	Single component System
Thinner	Clean Water
Thinning Ratio %	60-75

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice.