

TECHNICAL DATA SHEET

Sparco Series



Earthshine Texture Finish



Packing Size

6 & 24 kg

Handling

Handle with care, stir well before use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Health and Safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

Typical Paint System

| | |
|---------------------------|-------------|
| Earthshine Wall Primer | 1-2 Coats |
| Earthshine Wall Putty | If Required |
| Earthshine texture finish | 1 Coats |

Product Description

Earthshine texture is an acrylic based high quality thicksotropic paste, which is used to make different eyecatching textures for decorative purpose. Designs through different application techniques. It exhibits excellent adhesion, weather and water resistance. It contains anti fungal and anti bacterial additives. It can be over coated by any Sparco emulsion or enamel

Recommended use

Sparco texture finish is suitable for interior walls, ceilings made of cement plaster, cement rendering, asbestos or similar mineral substrate.

Film thickness and spreading rate

| | |
|----------------------------|---|
| Dry film thickness | 90-250 μ (depending upon application technique) |
| Wet film thickness | 150-400 μ |
| Theoretical Spreading Rate | 2-3 m ² /kg/coat |

Physical properties

| | |
|------------------|-----------|
| Colour | White |
| Finish | Matt |
| Volume solids | 70 % |
| Flash Point | N.A |
| Specific Gravity | 1.70-1.80 |

Surface Preparation

The substrate must be sound, clean, dry, free from dust, oil and grease etc. it can be either pre-primed or smooth surface. All traces of release agents must be removed. On chalky and dusty surfaces, all loose material must be removed by stiff bristle brushing.

Application methods



Special Roller



Hopper Gun

Drying Time

| Temperature | Touch Dry | Recoating Interval | Hard Dry |
|-------------|-----------|--------------------|----------|
| 23 °C | 1 hours | 4 hours | 6 Hours |
| 30 °C | 40 min | 3 hours | 4 Hours |
| 38 °C | 40 min | 2 hours | 3 Hours |

Application Data

| | |
|-------------------|--------------------------------------|
| System | Single component System |
| Thinner / Cleaner | Wash all equipments with clean water |
| Thinning Ratio % | Ready to use |

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice.