TECHNICAL DATA SHEET

Excellent Series







Packing Size

5.5, 20 Kg

Handling

Handle with care, stir well before use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Health and Safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

Typical Paint System

Sparco Water based Primer1-2 Coats

Sparco Excellent wall Putty 2-3 Coats

Sparco Excellent top coat (any) 2-3 Coats

Product Description

Sparco Excellent wall putty is a high PVC filler, which is specially formulated to fill porous interior structure.

Recommended Use

Recommended to fill pores & imperfections of Concrete, cement plaster, gypsum board & wood surfaces. Specially formulated for interior surface which gives smooth, easy to apply and an ideal finish for subsequent coats.

Film Thickness and Spreading Rate

Dry film thickness 100-300 μ (depending upon surface) Wet film thickness 150-400 μ Theoretical Spreading Rate 4-6 m²/kg/coat

Physical Properties

Colour White
Finish Matt
Volume solids 70 5
Flash Point N.A
Specific Gravity 1.65-1.80

Surface Preparation

The substrate must be sound, clean, dry, free from dust, oil and grease etc. it can be either pre-primed or smooth surface. All traces of release agents must be removed. On chalky and dusty surfaces, all loose material must be removed by stiff bristle brushing.

Application Methods





Drying Time

Temperature	Touch Dry	Recoating Interval	Hard Dry
23 °C	1 hour	4 hours	6 Hours
30 °C	40 min	3 hours	4 hours
38 °C	40 min	2 hours	2 Hours

Application Data

System	Single component System
Thinner	Wash all equipments with clean water
Thinning Ratio %	Ready to use