

# TECHNICAL DATA SHEET

Sparco Series



## Sparco Wall Putty



### Packing Size

1.5, 5.5 & 20 kg

### Handling

Handle with care. stir well before use

### Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

### Health and Safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

### Typical Paint System

Sparco Water based Primer	2-3 Coats
Sparco wall Putty	2-3 Coats
Sparco top coat (any)	2-3 Coats

### Product Description

Sparco wall putty is a high PVC ready to use filler, which is specially formulated to fill porous interior structure.

### Recommended Use

Recommended to fill pores & imperfections of concrete, cement, plaster, gypsum board & wood surfaces. Specially formulated for interior surface which gives smooth, easy to apply and an ideal finish for subsequent coats.

### Film Thickness and Spreading Rate

Dry film thickness	100-300 $\mu$ ( depending upon surface )
Wet film thickness	150-400 $\mu$
Theoretical Spreading Rate	4-6 m <sup>2</sup> /kg/coat

### Physical Properties

Colour	White
Finish	Matt
Volume solids	70 $\pm$ 5
Flash Point	N.A
Specific Gravity	1.65-1.80

### Surface Preparation

The substrate must be sound, clean, dry, free from dust, oil and grease etc. it can be either pre-primed or smooth surface. All traces of release agents must be removed. On chalky and dusty surfaces, all loose material must be removed by stiff bristle brushing.

### Application methods



### Drying Time

Temperature	Touch Dry	Recoating Interval	Hard Dry
23 °C	1 hour	4 hours	6 Hours
30 °C	40 min	3 hours	4 hours
38 °C	40 min	2 hours	3 Hours

### Application Data

System	Single component System
Thinner	Wash all equipments with clean water
Thinning Ratio %	Ready to use

#### DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice.