# **TECHNICAL DATA SHEET**

**Sparco Woodshelter Series** 



# Sparco Woodshelter Color Coat



#### **Packing Size**

0.91 & 3.64 Litres

# **Handling**

Handle with care. stir well before use

#### **Storage**

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

#### **Health and Safety**

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

## **Typical Paint System**

Sparco Woodshelter Sanding Sealer 2-3 Coats Sparco Woodshelter Color Coat 2-3 Coats Sparco Woodshelter Top Coat 2-3 Coats

# **Product Description**

Sparco woodshelter color coat is used to enhance the material beauty and shade of wood products. It has excellent gloss, durability, toughness, flow and leveling properties.

#### **Recommended use**

It is used on soft wood, hard wood, plywood, furniture, timberwork such as doors windows table cupboards etc.

## Film thickness and spreading rate

 $\begin{array}{ll} \text{Dry film thickness} & 20\text{-}25~\mu \\ \text{Wet film thickness} & 45\text{-}60~\mu \end{array}$ 

Theoretical Spreading Rate 15-17 m²/litre/coat

#### **Physical properties**

 $\begin{array}{lll} \mbox{Color} & \mbox{As per shade card} \\ \mbox{Finish} & \mbox{supper Gloss} \\ \mbox{Volume solids} & \mbox{45 \pm 2} \\ \mbox{Flash Point} & \mbox{38 °C} \\ \mbox{Specific Gravity} & \mbox{0.90 - 0.95} \\ \end{array}$ 

#### **Surface Preparation**

The substrate must be sound, clean, dry, free from dust, oil and grease etc. All traces of release agents must be removed. Wood should be properly sanded

# **Application methods**







Cloth Pac

#### **Drying Time**

Temperature	Touch Dry	Recoating Interval	Hard Dry
23 °C	3 Hours	10 Hours	16 Hours
30 °C	2 Hours	08 Hours	14 Hours
38 °C	1 Hour	06 Hours	12 Hours

# **Application Data**

System	Single component System
Thinner	Excellent Special MTT thinner
Thinning Ratio %	40-60 %